

What is claimed is:

1. A rubber composition blended with a rubber component-containing coagulated matter, wherein a rubber component is blended, and the rubber component comprises a component (A) comprising at least one of a natural rubber and a diene base synthetic rubber and a component (B) comprising a rubber component-containing coagulated matter obtained by drying and coagulating a serum of natural rubber obtained by centrifugally separating a natural rubber latex.

2. The rubber composition blended with a rubber component-containing coagulated matter as described in claim 1, wherein said component (A) is at least one selected from the group consisting of a natural rubber, an isoprene rubber, a styrene-butadiene copolymer rubber, a styrene-isoprene copolymer rubber and a butadiene rubber.

3. The rubber composition blended with a rubber component-containing coagulated matter as described in claim 1 or 2, wherein an amount of said component (B) is 0.5 to 40 % by weight based on the whole rubber components.

4. The rubber composition blended with a rubber component-containing coagulated matter as described in any of claims 1 to 3, wherein said component (A) is the styrene-isoprene copolymer rubber, and an amine base antioxidant is further blended.

5. A rubber composition, wherein a rubber component comprising a natural rubber is blended, and at least a part of the natural rubber is a natural rubber mixture [component (C)] obtained by coagulating a natural rubber latex at 90°C or higher, then turning it into crumbs and drying.

6. The rubber composition as described in claim 5, wherein said rubber component further comprises a diene base synthetic rubber.

7. The rubber composition as described in claim 5 or 6, wherein said diene base synthetic rubber is at least one selected from the group consisting of an isoprene rubber, a styrene-butadiene copolymer rubber and a butadiene rubber.

8. The rubber composition as described in any of claims 5 to 7, wherein an amount of said component (C) is 0.5 to

100 % by weight based on the whole rubber components.

9. The rubber composition as described in any of claims 5 to 8, wherein a viscosity stabilizer for a natural rubber is further added to said component (C).

10. The rubber composition as described in claim 9, wherein said viscosity stabilizer is a hydrazide compound represented by the following Formula (I):



wherein R in Formula (I) represents an alkyl group having 1 to 30 carbon atoms, a cycloalkyl group having 3 to 30 carbon atoms or an aryl group.

15 11. A production process for a rubber component-containing coagulated matter, comprising a step of centrifugally separating a natural rubber latex, a step of coagulating a resulting serum and a step of drying the coagulated serum.

20

12. A production process for a rubber component-containing coagulated matter, comprising a step of coagulating a natural rubber latex by vaporization, a step of turning a resulting coagulated matter into crumbs and a step of drying the coagulated matter turned into

25

crumbs.

13. The production process for a rubber component-
containing coagulated matter as described in claim 11 or
5 12, wherein said coagulating step is carried out by means
of any of a thin film distillation dryer, a drum dryer
and a belt dryer.

14. The production process for a rubber component-
10 containing coagulated matter as described in any of
claims 11 to 13, wherein said coagulating step is carried
out at 90°C or higher.

15. The production process for a rubber component-
15 containing coagulated matter as described in any of
claims 11 to 14, wherein said drying step is carried out
by means of a bucket type dryer or a belt type dryer.

16. The production process for a rubber component-
20 containing coagulated matter as described in any of
claims 11 to 15, further comprising a creper step and/or
a shredder step.